

PYRUS PANELS

Technical Data Sheet lisocore®

lisocore® RECOAT

(with melamine-faced cover layers)



Panel size: 2.800 x 2.070 mm

Tolerances:	Panel Thickness	EN 324	[mm]	± 0,2 without inlay ± 0,5 with inlay
	Length	EN 324	[mm]	± 5
	Width	EN 324	[mm]	± 5
	Squareness	EN 324	[mm/m]	± 2
	Warpage	EN 14322	[mm/m]	≤ 2

Technical Data:

Panel Thickness	Cover layer Thickness	Density	Bending Strength	Bending E-Modul
[mm]	[mm]	EN 323 [kg/m ³]	EN 310 [N/mm ²]	EN 310 [N/mm ²]
16,0	4,0	510	19	3200
19,0	4,0	430	20	3100
25,0	4,0	345	16	2800
38,0	8,0	330	8	1800
50,0	8,0	255	6	1400
60,0	8,0	215	4	1100

Available Colours:

Brilliant White 8681 SU	Front White 0101 SM; PE	Stone Grey 0112 PE	Light Vintage Oak 3025 SN	Graphite Grey 0162 PE	Anthracite 0164 PE
Gold Craft Oak K003 PW	Honey Castello Oak K358 PW	Amber Urban Oak K006 PW	Sand Barbera Oak K543 SN	Gold Baroque Oak K535 RW	Tobacco Franklin Walnut K547 RW

Formaldehyde: lisocore® is manufactured with E05 – compliant material.
FSC / PEFC: Order-related, we manufacture lisocore® with FSC / PEFC certification.
 Articles from the standard range do not have this certification in general.

This information is created internally, based on the standards mentioned above. We are happy to provide the test specifications for determining the technical data of lisocore®. We cannot accept any liability or give any guarantee for the correctness, completeness, and topicality. Our data sheets and product documents explicitly do not represent any legally binding assurance of the properties specified there. In particular, no suitability for a specific purpose can be derived from them. Furthermore, we explicitly refer to the general application of our general terms and conditions, which solely regulate all claims of the user upon purchase, unless otherwise expressly and individually agreed on between the user and Pyrus Panels GmbH.

Version 4/ 09.2023