PYRUS PANELS

Technical Data Sheet
Lisocore®

lisocore® with plywood cover layer
(E-Wood - Poplar - E-Wood)

Panel size: 2.440 x 1.220 mm

Tolerances:

Panel Thickness	EN 324	[mm]	± 0,2 without inlay ± 0,5 with inlay
Length	EN 324	[mm]	± 5
Width	EN 324	[mm]	± 5
Squareness	EN 324	[mm/m]	± 2
Warpage	EN 14322	[mm/m]	≤ 2

Technical Data:

Panel Thickness	Cover layer Thickness	Density	Bending Strength	Bending E-Modul
		EN 323	EN 310	EN 310
[mm]	[mm]	[kg/m³]	[N/mm²]	[N/mm²]
15,0	3,0	300	20 MD* 15 CD*	3400 MD* 3200 CD*

Formaldehyde: lisocore® is manufactured with E05 – compliant material.

*MD = Machine Direction, CD = Cross Direction

This information is created internally, based on the standards mentioned above. We are happy to provide the test specifications for determining the technical data of lisocore®. We cannot accept any liability or give any guarantee for the correctness, completeness, and topicality. Our data sheets and product documents explicitly do not represent any legally binding assurance of the properties specified there. In particular, no suitability for a specific purpose can be derived from them. Furthermore, we explicitly refer to the general application of our general terms and conditions, which solely regulate all claims of the user upon purchase, unless otherwise expressly and individually agreed on between the user and Pyrus Panels.

Version 01/2026

Pyrus Panels | Icom Advanced Materials GmbH
Betriebsstätte Bad Aibling
Carl-von-Ossietzky-Str. 17-21
83043 Bad Aibling

Handelsregister AG Eschwege HRB 3711
Steuernummer 026/236/00342
Umsatzsteuer ID Nr. DE451430360
Geschäftsführer: Ales Kopal

Bankverbindung:
Commerzbank AG
IBAN: DE04 5224 0006 0171 0516 00
BIC: COBADEFFXXX